

## ProGlass™ Silver

### Silver Reinforced Glass Ionomer Cement for Core Build up

ProGlass™ Silver is a mercury free fluoride releasing silver restorative. Designed to offer strong abrasion resistance, ProGlass™ Silver offers a unique blend of spherical silver-tin alloy with glass ionomer, providing an ultimate balance between working and setting time.

ProGlass™ Silver is ideal for lasting core build-ups, block-outs and repair and can also be used in cases where radiopacity is required.

#### INDICATIONS

Core build up material.

#### CONTRAINDICATIONS

- Pulp capping
- In rare cases the product may cause sensitivity in some people. If any such reactions are experienced, discontinue the use of the product and refer to a physician

#### ESSENTIAL INGREDIENTS

Barium, strontium aluminosilicate glass powder, Dried poly (acrylic acid), Aqueous solution of polyacids, silver alloy.

#### DIRECTIONS FOR USE

##### Tooth Preparation

- Prepare tooth using standard techniques. Extensive mechanical retention is not necessary.
- Rinse thoroughly and dry but do not desiccate. If desired, place a matrix band.

**Optional:** apply a 20% polyacrylic acid with a brush onto the wet enamel and dentin surfaces for 30 secs. Air dry gently for 10 seconds to remove the volatile components and to disperse the material. For pulp capping, apply a small amount of calcium hydroxide liner.

##### Dispensing and mixing

- To obtain a suitable consistency, mix powder and liquid according to the quantities indicated on the powder cap using the spoon included.
- Shake the bottle to loosen the powder. Overfill the spoon with the powder, level the spoon and place onto the mixing pad. Avoid compressing powder into the spoon.
- Turn the liquid bottle vertically with the tip about 5 cm above the mixing pad. Steady your hand and squeeze the bottle gently to dispense drops. If any bubbles are present, lightly tap the bottle with the fingers holding it. Discard drops that are obviously not full sized.
- After use, tightly close both bottles.
- Divide liquid and powder into 2 equal parts. Spread the liquid across the mixing pad and mix the first half with the whole of the liquid for 15 sec. add the second part and mix for 15 sec to obtain a homogeneous mixture. The mixed cement should be thixotropic and have a smooth consistency and glossy appearance. Total mixing time is 30 secs.

**Note:** Higher temperatures will shorten the working time, lower temperatures will prolong the working time. An overextended working time will cause the loss of adhesion to the dental enamel and the dentin.

##### Filling and Finishing

- Remove moisture from the cavity surface either with a cotton pellet or very gently with an air syringe. Do not desiccate the dentine and enamel surfaces.
- Place the mixed material into the cavity within the working time (1.30-2.00 min.) using a suitable placement. Make sure that no air bubbles will be incorporated.
- Form the contour
- Setting time is 3.5 minutes to 4 minutes from start of mixing.
- Use standard procedures for finishing

#### SHELF LIFE

The lot number & expiry date are indicated on the product. Do not use after expiry date.

#### PRECAUTIONARY INFORMATION FOR PATIENTS

Avoid use of this product in patients with known allergies to Glass Ionomers and / or Polyacrylic Acid. If prolonged contact with oral soft tissues occurs, flush with large amounts of water.

#### PRECAUTIONARY INFORMATION FOR DENTAL PERSONNEL

Do not mix the powder or liquid of ProGlass Silver with any other glass ionomer products. Use of protective gloves and a no touch technique is recommended.

In case of allergic reactions immediately stop the application and advise the patient to consult a physician.

Do not allow the cement mixture to contact the oral tissues or skin. In case of contact, remove the material with absorbent cotton soaked in alcohol and rinse with water.

In case of eye contact, immediately flush with water and seek medical treatment.

Direct contact with eugenol-based products is to be avoided. Eugenol slows the setting of glass ionomer cements.

#### CAUTION

U.S. Federal Law restricts this device to sale or use on the order of a dental professional.

#### STORAGE & DISPOSAL

Store in a cool and dark place / room temperature (5-30°C / 41-86°F) away from direct sunlight. Do not store material in proximity to eugenol containing material.

Protect powder from moisture and carefully close powder bottle after use.

See the Safety Data Sheet (available at [www.silmetdental.com](http://www.silmetdental.com) or through your local subsidiary) for disposal & safety information.

#### WARRANTY

Silmet Ltd. will replace product that is proven to be defective. Silmet Ltd. does not accept liability for any damage or loss, direct or consequential, arising from the use of or inability to use the product described. It is the responsibility of the dentist to determine before use, the suitability of the product for its intended use. The dentist assumes all risk and liability in connection therewith.

#### For instructions in additional languages:

- FR** Pour des instructions dans d'autres langues:
- DE** Die Anleitung in weiteren Sprachen:
- ES** Para obtener las instrucciones en otros idiomas:
- IT** Per istruzioni in altre lingue:



[www.silmetdental.com/downloads/downloads\\_instruction](http://www.silmetdental.com/downloads/downloads_instruction)



Silmet Ltd.

12 Hassadna st., Or-Yehuda, 6022011, Israel

Tel: 972-3-7353000, Fax: 972-3-5331581, [info@silmet.co.il](mailto:info@silmet.co.il), [www.silmetdental.com](http://www.silmetdental.com)

**EC** **REP** Obelis s.a

Bd. General Wahis 53. 1030 Brussels, Belgium

Tel: + (32) 2.732.59.54 Fax: + (32) 2.732.60.03, E-Mail: [mail@obelis.net](mailto:mail@obelis.net)