

CP385X
General Purpose Coex CPP Film Series

General Description

CP385X is a 5-layer coex CPP film offering high clarity & gloss. With added stiffness combined with good sealing performance on both sides, this film is suitable for VFFS applications.

TYPICAL PHYSICAL PROPERTIES (1.0MIL FILM)

PROPERTY	Units	ASTM Test#	Typical Value
Haze	%	D1003	2.0
Gloss	45 ⁰	D2457	85
Ultimate Tensile MD TD	psi	D882	6,500 5,500
Ultimate Elongation MD TD	%	D882	650 700
Secant Modulus MD TD	psi	D882	110,000 105,000
Coefficient Of Friction	gms	D1894	0.18
Yield	in ² /lb		30,800



CP385X 2-side sealable, slip modified on both surfaces.

Regulatory Compliance


- FDA 21 CFR 177.1520 (c)3.1a & (c)3.2a including food cooking applications under conditions of use A through H described in Table 2 of 21 CFR 176.170 (c).
- USPS-T-3204 Polywrap mailer overwrap.

TECHNICAL INFORMATION, RECOMMENDATIONS AND SUGGESTIONS HEREIN ARE FURNISHED WITHOUT CHARGE OR OBLIGATION. NO GUARANTEE IS MADE OF THEIR ACCURACY AND COPOL INTERNATIONAL LTD. ACCEPTS NO RESPONSIBILITY FOR RESULTS OBTAINED BY THE APPLICATION OF THIS INFORMATION OR THE SAFETY & SUITABILITY OF OUR PRODUCTS EITHER ALONE OR IN COMBINATION WITH OTHER PRODUCTS.

VALUES ARE TYPICAL DATA AND SHOULD NOT BE INTERPRETED AS SPECIFICATIONS BECAUSE CONDITIONS MAY VARY AND ARE BEYOND OUR CONTROL. USERS ARE ADVISED TO MAKE THEIR OWN DETERMINATION OF THE SAFETY AND SUITABILITY OF EACH PRODUCT IN THEIR OWN APPLICATION.

THERE IS NO WARRANTY AGAINST PATENT INFRINGEMENT. ALL PROPERTIES AND APPLICATIONS ARE PROVIDED AS INFORMATION ONLY AND THERE ARE NO WARRANTIES EXPRESSED OR IMPLIED OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE.

Typical Film Section



Sealant Layer = RACO PP
Core Layer = HP PP