

**CP301XCT - Developmental  
Co-Ex CPP Film**

**General Description**

CP301XCT is a Co-Ex CPP film blend that offers good cold temperature performance while maintaining clarity, gloss and heat sealing performance. This CPP product is slip modified for machinability and is heat sealable on both surfaces.

TYPICAL PHYSICAL PROPERTIES (1.25 MIL FILM)

PROPERTY	Units	ASTM Test#	Typical Value
Haze	%	D1003	2.5
Gloss	45 <sup>0</sup>	D2457	82
Tensile MD	psi	D882	4,655
Tensile TD			6,120
Elongation MD	%	D882	1036
Elongation TD			732
Secant Modulus MD	psi	D882	47,427
Secant Modulus TD			48,152
Coefficient Of Friction	gms	D1894	0.18
Yield	in <sup>2</sup> /lb		24,640



**Regulatory Compliance**

- FDA 21 CFR 177.1520  
(c)3.1a food contact only

TECHNICAL INFORMATION, RECOMMENDATIONS AND SUGGESTIONS HEREIN ARE FURNISHED WITHOUT CHARGE OR OBLIGATION. NO GUARANTEE IS MADE OF THEIR ACCURACY AND COPOL INTERNATIONAL LTD. ACCEPTS NO RESPONSIBILITY FOR RESULTS OBTAINED BY THE APPLICATION OF THIS INFORMATION OR THE SAFETY & SUITABILITY OF OUR PRODUCTS EITHER ALONE OR IN COMBINATION WITH OTHER PRODUCTS.

VALUES ARE TYPICAL DATA AND SHOULD NOT BE INTERPRETED AS SPECIFICATIONS BECAUSE CONDITIONS MAY VARY AND ARE BEYOND OUR CONTROL, USERS ARE ADVISED TO MAKE THEIR OWN DETERMINATION OF THE SAFETY AND SUITABILITY OF EACH PRODUCT IN THEIR OWN APPLICATION.

THERE IS NO WARRANTY AGAINST PATENT INFRINGEMENT. ALL PROPERTIES AND APPLICATIONS ARE PROVIDED AS INFORMATION ONLY AND THERE ARE NO WARRANTIES EXPRESSED OR IMPLIED OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE.

**Typical Film Section**

