



Greenhouse Cover



Type SUNCOVER NECTARINE DIFFUSED / C 980



Film usage Greenhouse cover

Width Up to 15 meters

Thickness 200 micron

Length As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	22
	TD		MPa	21.5
Elongation at break	MD		%	700
	TD		%	750
Tear resistance	MD	ASTM D-1922	Gr./mm	9000
	TD		Gr./mm	12000
Falling dart drop impact		ASTM D-1709	Gram	1000
Light transmission in PAR	%	ASTM D-1003		89
Diffused light tr .in PAR	%			60
UV – trans. 300 – 380 nm.	%			80
				Typical values

