



Greenhouse Cover



Type SUNSAVER 4 (EVA) / C 704

Film usage Greenhouse cover
Width Up to 15 meters
Thickness 200 micron
Length As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	21
	TD		MPa	22.5
Elongation at break	MD		%	650
	TD		%	800
Tear resistance	MD	ASTM D-1922	Gr./mm	5000
	TD		Gr./mm	6000
Falling dart drop impact		ASTM D-1709	Gram	1400
Light transmission in PAR	%	ASTM D-1003		90
Diffused light tr .in PAR	%			15
Thermicity 7-15 micron	%	Internal "FT-IR"		85
Anti Drip				Yes (place in accordance to instruction)
				Typical values

