



Greenhouse Cover



Type SUNSAVER 504 / C 779

Film usage	Greenhouse cover
Width	Up to 15 meters
Thickness	200 micron
Length	As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	22
	TD		MPa	21.5
Elongation at break	MD		%	680
	TD		%	730
Tear resistance	MD	ASTM D-1922	Gr./mm	7000
	TD		Gr./mm	11000
Falling dart drop impact		ASTM D-1709	Gram	1000

Light transmission in PAR	%	ASTM D-1003		87
Diffused light tr .in PAR	%			60
UV – trans. 300 – 380 nm.	%			0
Thermicity 7-15 micron	%	Internal "FT-IR"		88
Anti Drip				Yes (place in accordance to instruction)
				Typical values

