



Mulch film



Type BLACK / WHITE ORCHARD / C 902

Film usage	Ground cover
Width	Up to 10 meters
Thickness	150 micron
Length	As required



		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	32
	TD		MPa	30
Elongation at break	MD		%	750
	TD		%	850
Tear resistance	MD	ASTM D-1922	Gr./mm	14000
	TD		Gr./mm	20000
Falling dart drop impact		ASTM D-1709	Gram	1400
Light transmission in PAR	%	ASTM D-1003		0
Reflection in PAR	%			75
				Typical values

