




Casey Concrete Ltd. 445 x 445 mm (18 x 18 in.) EC STONE

caseyltd.ca



PLEASE NOTE:

Products are made from natural material sources and therefore colour variations are common. Efflorescence is also a common occurrence with all concrete and concrete products. Efflorescence does not affect the quality of the product and will fade over time or can be removed with cleaning products.

DIMENSIONAL TOLERANCES:

Meets the requirements of CSA A165.1 Concrete Masonry
 Length: +/- 3 mm (+/- 0.12 in.)
 Width: +/- 3 mm (+/- 0.12 in.)
 Height: +/- 3 mm (+/- 0.12 in.)

PHYSICAL PROPERTIES:

Meets the requirements of CSA A165.1 Concrete Masonry
 Compressive Strength: Min 25 MPa @ 28 Days
 Absorption (%): 8% Maximum @ 28 Days

AVAILABILITY:

Available in Smooth and Slate finishes

DE-ICING SALT DURABILITY MASS LOSS (max.):

225 g/m² after 28 cycles, or
 500 g/m² after 49 cycles

