





# Casey Concrete Ltd. GRASS PAVING STONE 400 x 400 x 80 mm (16 x 16 x 3 H in.)

caseyltd.ca



### PLEASE NOTE:

Products are made from natural material sources and therefore colour variations are common.  
 Efflorescence is also a common occurrence with all concrete and concrete products.  
 Efflorescence does not affect the quality of the product and will fade over time or can be removed with cleaning products.

### DIMENSIONAL TOLERANCES:

Meets the requirements of  
 CSA A231.2 Concrete Pavers  
 Length: -1 to +2 mm    Width: -1 to +2 mm  
 Height: -3 to +3 mm

### PHYSICAL PROPERTIES:

Meets the requirements of CSA A231.2 Concrete Pavers  
 Compressive Strength: Min. 50 MPa @ 28 Days  
 Absorption (%): 5.5% Maximum @ 28 Days  
 Freeze/Thaw: Not exceed 1% weight loss

### PER UNIT:

Weight Per Piece: 18.15 kg (40 lbs)  
 Area: 0.16 m<sup>2</sup> (1.72 ft<sup>2</sup>)  
 Pieces Per Pallet: 48

### DE-ICING SALT DURABILITY MASS LOSS (max.):

225 g/m<sup>2</sup> after 28 cycles, or  
 500 g/m<sup>2</sup> after 49 cycles

