





Casey Concrete Ltd. 98x198 mm (4x8 in.) BORDER STONE

caseyltd.ca



DE-ICING SALT DURABILITY MASS LOSS (max.):

225 g/m² after 28 cycles, or 500 g/m² after 49 cycles

PLEASE NOTE:

Products are made from natural material sources and therefore colour variations are common. Efflorescence is also a common occurrence with all concrete and concrete products. Efflorescence does not affect the quality of the product and will fade over time or can be removed with cleaning products.

PACKAGING

Pieces Per Pallet: 480
Weight Per Piece: 2.73 kg (6 lbs)
Weight Per Pallet: 1310 kg (2880 lbs)
Coverage Per Pallet: 103.3 sq. ft

DIMENSIONAL TOLERANCES:

Meets the requirements of CSA A231.2 Concrete Pavers
Length: -1 mm to +2 mm
Width: -1 mm to +2 mm
Height: -3 mm to +3 mm

AVAILABILITY:

Available in smooth top surface
Available in 60 mm thickness

PHYSICAL PROPERTIES:

Meets the requirements of CSA A231.2 Concrete Pavers
Compressive Strength: Min 50 MPa @ 28 Days
Absorption (%): 5.5% Maximum @ 28 Days
Freeze/Thaw: Not exceed 1% weight loss

