

US CONSTRUCTION FABRICS LLC

8 Ledge Rd, Windham, NH 03087

(603) 893-5480, Fax (603) 893-2154

www.usconstructionfabrics.com

Wholesale Distribution

CONSTRUCTION FABRICS, LINERS, & ENVIRONMENTAL PRODUCTS

ECC-2B™ Double Net Coconut Biodegradable Rolled Erosion Control Product

Description:

The ECC-2B™ is made with uniformly distributed 100% coconut fiber and two organic jute nets securely sewn together with biodegradable thread. The tightly compressed blankets are wrapped and include a product label, code and installation guide. The blankets are palletized for easy transportation. The ECC-2B™ has functional longevity of approximately 24 months, but will vary depending on soil and climatic conditions, and is suitable for slopes 1:1 and medium to high flow channels. The ECC-2B™ meets Type 4 specification requirements established by the Erosion Control Technology Council (ECTC) and Federal Highway Administration's (FHWA) FP-03 Section 713.17.

IVIALITIX:		<u> </u>		
	100% Coconut			
Netting:	Туре		Net Color	
Top: Organ	nic Leno Weave Jute		Natural	
Middle: None				
Bottom: Organ	nic Leno Weave Jute			
Net Opening:	Тор	Middle	Bottom	
	0.5" x 1.0"		0.5" x 1.0"	
Thread:	Туре	Color		
	Biodegradable Thread	Natural		
Roll Sizes:	Standard	"A" Size	Mega	
Width:	7.5 ft 2.3 m	3.75 ft 1.1 m	15 ft 4.6 m	
Length:	120 ft 36.6 m	240 ft 73.2 m	120 ft 36.6 m	
Weight <u>+</u> 10%:	60 lbs 27.2 kg	60 lbs 27.2 kg	120 lbs 54.4 kg	
Area:	100 yd² 83.6 m²	100 yd ² 83.6 m ²	200 yd² 167.2 m²	
#/Pallet:	16	6	16	

Index Value Properties*:						
Property	Test Method	Ty	pical			
Mass/Unit Area	ASTM D6475	9.50 oz/yd ²	322.1 g/m2			
Thickness	ASTM D6525	0.25 in	6.35 mm			
Tensile Strength-MD	ASTM D6818	240 lb/ft	3.50 kN/m			
Elongation-MD	ASTM D6818	11 %				
Tensile Strength-TD	ASTM D6818	164 lb/ft	2.39 kN/m			
Elongation-TD	ASTM D6818	16.0 %				
Light Penetration	ASTM D6567	17 %				
Density / Specific Gravity	ASTM D792	N/A %				
Water Absorption	ASTM D1117	340 %				
*May differ depending upon raw material variations						

^{&#}x27;May differ depending upon raw material variations

Value
0.04
≥ 2:1
0.102
0.120
0.134

^{*}Large-Scale Results obtained by 3rd Party GAI Accredited Independent Laboratory

Test Method	Parameters	Results
	50mm (2in) / hr-30 min	SLR**=14.16
ECTC Method 2 Rainfall	100mm (4in) / hr-30 min	SLR**=18.25
	150mm (6in) / hr-30 min	SLR**=23.24
ECTC Method 3 Shear Resistance	Shear at .50 in soil loss	2.76 lb/ft ²
ECTC Method 4 Germination To	p soil; Fescue; 21 day incub	ation 501 %
*Bench scale tests should not be u	used for design purposes.	
**Soil Loss Ratio=Soil Loss Bare So	oil/Soil Loss with RECP=1/C-	Factor

^{***}The preceding test data excerpts were reproduced with the permission of AASHTO, however, this does not constitute endorsement or approval of the product, material or device by AASHTO

Channel Performance Design Values*:								
Property	Test Method	Value						
Unvegetated Shear Stress	ASTM D 6460	2.25	lbs/ft ²	107.73	Pa			
Unvegetated Velocity	ASTM D 6460	9.0	ft/s	2.74	m/s			
Vegetated Shear Stress	NA	N/A	lbs/ft ²	N/A	Pa			
Vegetated Velocity	NA	N/A	ft/s	N/A	m/s			
Manning's N (Value Represe		0.02	25					
*Large-Scale Results obtain	ed by 3 rd Party GA	I Accred	ited Inde	pendent				









Laboratory