



**DETALE  
CPH**

# KC14

---

Easy to apply and pleasing to your senses.  
Share your story #detalecph



## **Del dit DETALE-projekt** <sup>DK</sup>

---

Del dit helt eget DETALE projekt eller find massevis af inspiration i andres projekter på Instagram under #detalecph. Vi modtager meget gerne billeder til deling på [hello@detalecph.com](mailto:hello@detalecph.com)

## **Del ditt DETALE-prosjekt** <sup>NO</sup>

---

Del ditt helt eget DETALE prosjekt eller finn masse inspirasjon i andres prosjekter på instagram under #detalecph. Vi vil gjerne motta bilder som vi kan dele, på [hello@detalecph.com](mailto:hello@detalecph.com)

## **Dela ditt DETALE-projekt** <sup>SE</sup>

---

Dela ditt helt eget DETALE-projekt eller hitta massor av inspiration i andras projekt på instagram under #detalecph. Vi tar gärna emot bilder för delning på [hello@detalecph.com](mailto:hello@detalecph.com)

## **Share your DETALE-project** <sup>UK</sup>

---

Share your DETALE project or find lots of inspiration from other projects on instagram #detalecph. We are happy to receive pictures to share at [hello@detalecph.com](mailto:hello@detalecph.com)

## **You need**

---

2 spatulas of 15-35 cm in size  
Sandpaper grain 180-220  
Shielding e.g. plastic or cardboard and masking tape  
1 soft duster  
Microfiber cloth for Topcoat (opt. hand sprayer)  
Gloves and respiratory protection for sanding

## **Preparation**

---

The surface on which KC14 is to be applied has to be smooth, dry, equally absorbent and sustainable. If in doubt, you should prime the base before beginning. It is important to carefully cover in order to avoid unwanted spots. Topcoat in unwanted spots, is very hard to remove. The process of sanding will produce dust.

## **Durability and maintenance**

---

KC14 is fully hardened after 2-3 weeks. Be aware that the wall will never become rock hard and therefore is receptive to scratches ect. With the second layer of Topcoat you obtain a dirt repellent surface corresponding to a gloss 10 paint, meaning that the surface can be washed as instructed above. We do not recommend using KC14 Classic and KC14 Raw on backsplashes, as the surface will not be resistant towards hot splashes.

KC14 can be maintained with Topcoat. Add 5-10% Topcoat to your wash water when needed. In addition, the wall is cleaned with mild detergents.

Enjoy your KC14 project. Remember to enjoy the creative process as much as your personal result.



# 1

Set up masking tape around the desired area to cover. Apply KC14 on the entire area at once. The plaster should have a thickness of 2-3 mm. with a smooth covering layer. If the layer is not smooth, plaster spots will be noticeable in the final result. Remove the masking tape before the plaster dries. The plaster has to dry for a minimum of 16 hours.

**Tip: The finish depends on the way you apply the plaster. Avoid applying in straight lines, but with smooth and soft curves. Bubbles can appear and are part of the natural look.**

# 2

If the plaster appears with irregularities or knobs, sand these away before second layer is being applied. We recommend to use grain 180 for this. Dust off the area by using a soft duster.

Set up masking tape again and apply KC14 Classic on the entire area at once. The second layer must not be too thin as it will increase the risk of sanding through the surface and leave noticeable marks. Remove the masking tape before the plaster dries. The plaster has to dry for a minimum of 16 hours.

# 3

Make sure that the plaster is totally dry before you start sanding. Do also make sure to cover furniture etc. carefully given that sanding produces a lot of dust. Gently, sand the area, with circled movements, using grain 180-220 until the surface is uniform. Again, avoid sanding through the surface as clearly noticeable marks will appear. Sanding machines cannot be used! Dust the whole area thoroughly with a soft duster. Remain all covering for the next step, as unwanted Topcoat stains are very difficult to remove.

# 4

Set masking tape up again. Apply Topcoat twice by using the microfiber cloth to dab it on with an interval of 1-2 hours. The entire area has to be coated at once. Runners are visible and must be avoided. Let the Topcoat dry for 2-3 hours before sanding the area with grain 220 to achieve smoothness. Dust off the area using a damp cloth.

**Tip: Hand sprayer can be used. Do only spray small areas at a time and make sure to immediately dab the area with a microfiber cloth before the Topcoat dries. A third layer can be applied if the area is exposed to much wear.**

detalecph.com

@detalecph

hello@detalecph.com