

Description

STIFERITE ALE is a high performance insulation board manufactured from CFC or HCFC free closed cell rigid polyisocynurate PIR foam. It's covered with an 80 µm embossed aluminum foil and a 200 µm embossed aluminum foil.

■ GUIDELINE for drafting of technical specifications

Thermal insulation STIFERITE ALE in polyiso rigid foam (PIR) of thickness...(*), covered on one side with an 80 µm embossed aluminum foil and a 200 µm embossed aluminum foil, has:

... (it is recommended to fill in the tendering specifications indicating the features and performance more relevant for the specific application)

Product of company certified according to quality management system UNI EN ISO 9001:2008, Environmental Management System UNI EN ISO 14001:2004, occupational Health and Safety Management OHSAS 18001:2007.

(*) Parameters change according to panel thickness. To determine the values corresponding to the used thickness, please use the specifications indicated on this technical sheet.

Dimensions

Width and length 1200 x 4000 mm

Thickness

20 mm and 30 mm

Main application

For the costruction pre-insulated aluminum ducts for air distribution

MAIN CHARACTERISTICS AND PERFORMANCES

insulating material density - ρ [kg/m³]

EN 1602 - average value 45 ± 3.0

Average thermal conductivity - $\lambda_{9090,1}$ [W/mK]

EN 13165 Annex A and C Value determined 10° C 0.021

Resistance against pressure

The duct resists at the maximum pressure of 3750 Pa

Air leakage classification

EN 13403, EN 1507

Stiferite duct constructed using bayonet profiles is in B class

European fire reaction- Stiferite duct EN 13501-1, EN 11925-2, EN 13823

B s2 d0

British fire reaction class - Stiferite board

BS476: part 6:1989 0 Class

BS476: part 7:1997 1 Class

BS476: part 6/7

0 Class

Rigidity class EN 13403

300.000 (R5)

Acoustic experimental values - dB **EN ISO 7235** Insertion loss in octave band

	Duct Dimensions 200 x 200 1 m	Duct Dimensions 400 x 400 1 m	Duct Dimensions 600 x 600 1 m
Frequency Hz	dB	dB	dB
63	1,4	1,8	0,1
125	0,6	1,5	3,2
250	0,7	4,0	1,7
500	3,3	1,3	1,0
1000	2,4	1,0	0,9
2000	1,3	1,0	0,7
4000	1,2	0,7	0,6
8000	2,3	1,6	1,2

Blowing agent EN 15804

OPD (ozone depletion potential) = 0 and GWP (global warming potential) does not include in CML ĬA:2016

Tolerance [mm]

EN 13165 width and lenght

± 7,5 for 1200mm

± 10 for 4000 mm

Thickness

±1 mm



NOTES

Stability to the temperature

Stiferite panels are used in a range of continous temperatures normally included between -40° Cand +110° C. Long exposures to the temperatures could cause deformations to the foam or to the coats, but without causing sublimation or fusion.

Aspect

Prolunged exposure of the polyurethane foam to UV rays can cause surface oxidation, the phenomenon does not affect the basic characteristics and performance of the panel.

■ Packaging & Storage

The Stiferite panels of standard sizes are normally packed in PE, in closed packaged and labeled. Store the packages off the ground. Store them for long periods indoor and dry.

Warning

The data reported in this document is binding on the features and beneficts provided. Other features and additional informationcan also be changed in the absence of specific signals.

Other information

Call Stiferite technical office ph. +39 0498997911