

**Eterna-Seal**  
**ACRYLIC BRUSH GRADE MASTIC**  
**8102**



**PHYSICAL PROPERTIES :**

An acrylic flexible liquid membrane coating specially formulated for use on concrete block, masonry, stucco, and where aesthetic appearance of the building is desired. The white or pastel colors reflect the sun's rays and allow the surface to remain cool, thus saving energy. Refer to published guide specifications for additional details.

**SPECIFICATIONS**

Flash Point	None
Wt./Gal. (Approx.)	12.4#
Viscosity @ 80°F	125 +/- 5 KU
Non-Volatile (Fed. Test Method 141)	65% Minimum
Percent Latex Solids	20% Minimum
Percent Solids by Volume	60% Minimum
Dry Film Thickness of 1 gal/100 sq. ft. (Less Absorption by Surface)	8 Mils
Drying Time (to touch) on metal	1 ½ hours
(thorough) on metal (77°F., 50% RH)	3 ½ hours
Cold Temperature Flex. 1" Mandrel @ 0°F	No Cracks
Service Temperature Extended Exposure	-30 to 200°F
Ultra Violet Light Resistance	Excellent
Discoloration under Ultra Violet Light	None
Effect of Weathering	Slight Chalking
Resistance to Rainfall, after thoroughly dry (Minimum 8 hours @ 77°F)	Excellent
Freeze – Thaw Stability	Excellent
Elongation to Break	300%
Tensile Strength	250 psi
Fungus resistance	Passes
Perm Rating	5.0 U.S. Perms
Chemical Resistance to mild acid & alkali fumes	Good
Recoat @ 80°F	Overnight
Solar Reflectance	80% Min.

8102