

TRU-LASTIC SEAM-SEALER CAULK 7175



PHYSICAL PROPERTIES :

Tru-Lastic Seam Sealer Caulk is a one part, high performance sealant. The cured sealant exhibits good physical properties including excellent adhesion to a variety of construction material including marine surfaces. Tru-Lastic possesses rubber-like characteristics and can be compressed or extended. Refer to published guide specifications for additional details.

SPECIFICATIONS

Flash Point	105°F
% Solids	60 ± 2%
Application	Trowel
Film Thickness of 1 gallon	10 mils, 100sq.ft
Elongation at 72°F	400% Min.
Recovery from 400% Elongation	90%
100% Elongation	100%
Temperature Range	-30° to 200°F
Application Range	40° to 100°F
Dry to touch	4 to 24 hours
Dry throughout	30 days
Total Cure Time	45 to 60 days
Tensile Strength	600 psi min.
Compatibility with old asphalt built-up roof	Excellent
Weight/gallon	9.2 lbs.
Viscosity	Heavy paste
Moisture Vapor Transmission, Perms	.15

7175