

# Corr-Ze™ 100

## Soluble Salt and Contaminant Remover



### PRODUCT DESCRIPTION

Non-toxic soluble salt remover

### INTENDED USES

For application to a wide variety of substrates in conjunction with hand and power tool cleaned steel, pressure washed steel at pressures of 3500 to 5000 psi. Vapor blast, conventional abrasive blast cleaned and Ultra High Pressure Water “UHP” blast cleaned steel. Corr-Ze™ 100 can be used anywhere a protective coating will be applied to a metal substrate and extended coating service life is desirable. Coatings applied over Corr-Ze™ 100 cleaned surfaces significantly outperform coatings which are applied over substrates prepared only by means of conventional surface preparation standards. Corr-Ze™ 100 is “coating-neutral,” does not leave any residue, and is not a film-former. It can be used with any coating system and is an excellent remover of soluble salts and other non-visible contaminants in industrial, offshore structures, pulp and paper plants, bridges, and environments in both atmospheric exposure and immersion service systems.

### ALTERNATIVE USES

Corr-Ze™ 100 can be used with a pressure washer for pre-cleaning to remove existing soluble contaminants or in accordance with SSPC SP1 for removing soil, dirt, dust, residual abrasives, mud, chalking coatings, airborne contaminants, pollen, heavily flaking non-adhesion coatings, or other visible contaminants. Oil, grease, or other petroleum products should be removed using alternative detergents like solvents or degreasers.

### Corr-Ze™ 200

<b>Physical Data</b>	Liquid material supplied in a 5-gallon pails.
<b>Color</b>	Clear, very light amber liquid
<b>Viscosity</b>	None, water-like
<b>Dilution Ratio</b>	1:100 to 1:200
<b>Equipment Dilution Ratios</b>	Vapor blast, after UHP and conventional abrasive blast: 1:100 UHP water blasting “when injected”: 1:200
<b>Mix Ratio</b>	1.28 ounces to 1 gallon of water used in equipment at 1% dilution
<b>Mixing</b>	1 gallon of Corr-Ze™ 100 to 100 gallons of preferably deionized water (1% solution) or fresh, clean potable water. Consult the manufacturer’s representative for use of alternative water sources.
<b>Method of Application</b>	Injection by incorporating into blast stream of vapor blast, and Ultra High Pressure Water Blasting and after hand / power tool cleaning and after conventional abrasive blasting and UHP blasting
<b>Drying Time</b>	Surfaces treated with Corr-Ze™ 100 solution will dry to touch within 20-30 minutes depending on relative humidity, wind, and air movement, air temperature, and substrate temperature. Corr-Ze™ 100 washed surfaces may be coated as soon as the substrate is dry. In cool, humid conditions drying time may be accelerated by increasing air flow over the substrate. Be careful not to contaminate the surface. Deposition of atmospheric contaminants may settle on the Corr-Ze™ 100 prepared surface if left exposed and uncoated.

### Targeting Corrosion at its Core™



# Corr-Ze™ 100

Soluble Salt and Contaminant Remover



---

<b>Corr-Ze™ 200</b>	<b>Pot Life</b>	Corr-Ze™ 100 working pot life is 30 days, depending on water quality. Mix only as much Corr-Ze™ 100 as needed for the project. The ready-to-use Corr-Ze™ 100 should be used within thirty days of mixing.
	<b>Clean Up</b>	Thoroughly flush all equipment with potable water according to normal maintenance procedures. Dispose of clean up waste in accordance with all local ordinances.
	<b>Appearance After Application</b>	After drying, carbon steel surfaces prepared with Corr-Ze™ 100 may exhibit a variety of appearances, from a bright, mirror-like finish to a dull gray appearance. Such variation is normal and depends on the composition of the steel, method of surface preparation, anchor profile (if any), and other factors. Effectiveness of the Corr-Ze™ 100 process may be confirmed by testing the surface for residual salts using industry approved methods.

---