

# PEAKMOOR SANDSTONE



This data sheet was compiled by the Building Research Establishment (BRE). The data sheet was compiled in November 1997 and updated in June 2000 using BRE test results and data collected in earlier surveys. The work was carried out by BRE as part of a Partners in Technology Programme funded by the Department of the Environment, Transport and the Regions and Blockstone Ltd and does not represent an endorsement of the stone by BRE.

### Safety in Use

Slip Resistance (Note 1)	Not determined	Values > 40 are considered safe.
Abrasion Resistance (Note 1)	Not determined	Values <23.0 are considered suitable for use in heavily trafficked areas.

### Strength under load

1) Compression (Note 2)	72.5 MPa	Loaded perpendicular to the bedding plane ambient humidity
2) Bending (Note 1)	7.5 MPa	Loaded perpendicular to the bedding plane ambient humidity
	4.8 MPa	Loaded parallel to the bedding plane ambient humidity

### Porosity and Water Absorption

1) Porosity (Note 3)	16.46%	
2) Bending (Note 1)	0.68	
3) Water Absorption	5.07 % (by wt)	
4) Bulk specific gravity	2210kg/m3	

### Resistance to Frost

Freeze/Thaw Test (Note 1)	Not determined	Note: the stone Passed Test B using DIN 52 104
---------------------------	----------------	--

### Resistance to Salt

Sodium Sulphate Crystallisation Test (Note 3)	1.07% Mean wt loss	
Sodium Sulphate Crystallisation Test (Note 14) (saturated)	No results available	

### Resistance to Acidity

Acid Immersion Test (Note 4)	Pass	All samples passed the test with no splitting or delamination
------------------------------	------	---

(Test methods Note 1 = prEN1341, Note 2 = prEN 1342, Note 3 = prEN 1341 /BRE 141, Note 4 = BRE 141, Note 5 = ASTM. Based on BRE Test results and data supplied by the producer)

### General

The quarry is on Stanton Moor on the eastern outskirts of Stanton-in-Peak, near Matlock in Derbyshire. The quarry was reopened in 1985 but it has been producing building stone since at least 1945. There are good reserves of stone.

### Petrography

Peakmoor Sandstone is a Millstone Grit of Carboniferous age. It is a fine- to medium-grained stone, and varies in colour from light brown to pink. Stone is extracted from a 20m high face with average block sizes of 1500mm x 800mm 800mm.

### Expected Durability and Performance

It is important that the results from the individual tests are not viewed in isolation. They should be considered together and compared to the performance of the stone in existing buildings and other uses. Carboniferous Sandstones are traditionally acknowledged as generally being a very durable building and paving stone and have been used extensively in many towns and cities in the UK. Peakmoor Sandstone appears to be a durable stone that is not effected by acid rain or air pollution. Most sandstones have good frost resistance. The compressive strength of the stone is typical of the range for sandstones and is comparable with the stronger UK limestones. It is accepted in Germany for use in rainscreen type cladding at 40mm thick.

Overall, Peakmoor Sandstone should be suitable for use in most aspects of load bearing masonry and cladding.



## Quarry Location

**Bolehill Quarry,  
Wingerworth,  
Derbyshire,  
S42 6RG**

## RGB Landscapes

**Ropewalk House,  
2 Cottage Terrace,  
Nottingham,  
NG1 5DX**

**T: 0115 985 9100  
E: sales@rgblandscapes.co.uk**

**www.rgblandscapes.co.uk**



# STANTON MOOR SANDSTONE



This data sheet was compiled by the Building Research Establishment (BRE). It is based on data from tests carried out by other test laboratories, collated BRE data and from current tests at BRE (1997 and 2000). The data sheet was compiled in July 1997 and updated in May 2000. The work was carried out by BRE as part of a Partners in Technology Programme funded by the Department of the Environment, Transport and the Regions and Stancliffe Stone Company Ltd and does not represent an endorsement of the stone by BRE.

## Safety in Use

Slip Resistance (Note 1)	Wet: 70	Values > 40 are considered safe.
Abrasion Resistance (Note 1)	20.1 (20.1-22.6 range)	Values <23.0 are considered suitable for use in heavily trafficked areas

## Strength under load

1) Compression (Note 2)	79.0 MPa	Loaded perpendicular to the bedding plane ambient humidity
2) Bending (Note 1)	8.9 MPa	Loaded perpendicular to the bedding plane ambient humidity
	Not tested	Loaded parallel to the bedding plane ambient humidity

## Porosity and Water Absorption

1) Porosity (Note 3)	14.8%	
2) Bending (Note 1)	0.67	
3) Water Absorption	4.4% (by wt)	
4) Bulk specific gravity	2259kg/m <sup>3</sup>	

## Resistance to Frost

Flexural strength after Freeze/Thaw Test (Note 1)	7.9 MPa	Loaded perpendicular to the bedding ambient humidity
---	---------	--

## Resistance to Salt

Sodium Sulphate Crystallisation Test (Note 3)	8.46% Mean wt loss	
---	--------------------	--

## Resistance to Acidity

Acid Immersion Test (Note 4)	Pass	
------------------------------	------	--

## General

The quarry is on the southern outskirts of the village of Stanton-in-Peak near Matlock. The site is off the Birchover Road. The present quarry was re-opened in 1983. Blocks are available up to 12 tonnes in weight with block sizes 1.5 x 3 x 3 m. Depths on bed vary from 1.5 - 3.6 m with lengths 0.7 - 1.8 m. Sawn material is produced at the stoneworks of Stancliffe Stone Company Ltd.

## Petrography

Stanton Moor is a buff and pink/buff fine to medium grained sandstone from the Carboniferous Millstone Grit series.

## Expected Durability and Performance

It is important that the results from the from individual tests are not viewed in isolation. They should be considered together and compared to the performance of the stone in existing buildings and other uses. Sandstones from the Millstone Grit series are traditionally acknowledged as generally being a very durable building and paving stone and have been used extensively in many towns and cities in the UK. Stanton Moor sandstone appears to be a durable stone that is not effected by acid rain or air pollution. The weight lost in the harsh saturated sodium sulphate crystallisation test indicates limited resistance to salt damage in very severe environments (for example in coastal locations or from de-icing salts); the results suggest that the stone would have good frost resistance. The compressive strength of the stone is typical of the range for comparable with sandstone. The flexural strength is towards the lower end of the range for sandstones and if used for paving then the units may need to be thicker than those for some other sandstones. The abrasion resistance is comparable with York paving stones and should be suitable for use in heavily trafficked areas.

Overall, Stanton Moor should be suitable for use in most aspects of construction including flooring, paving, load bearing masonry and cladding. Traditional usage is for walling and dressed stone. The stone may not suitable for areas where a long service life or exposure to salts is required.

(Test methods Note 1 = EN1341, Note 2 = EN 1342, Note 3 = EN 1341 /BRE 141, Note 4 = BRE 141)

Tests were carried out at BRE in 1997 and 2000.

Please note that stone is a natural product and all results are subject to variation



## Quarry Location

Dale View/Palmer's Quarry.  
Grangemill,  
Matlock,  
Derbyshire,  
DE4 4BW

## RGB Landscapes

Ropewalk House,  
2 Cottage Terrace,  
Nottingham,  
NG1 5DX

T: 0115 985 9100  
E: sales@rgblandscapes.co.uk

[www.rgblandscapes.co.uk](http://www.rgblandscapes.co.uk)