

DRYMiX®

Dry Décor 301

Cement based, high quality, ready mixed color decorative smooth finish façade renders suitable for extreme weather conditions.

Description:

Dry Decor 301 is cement based, high quality, extreme weather resistant, color stable, decorative façade renders in powder form. Dry Décor 301 requires the addition of water on site.

Dry Décor 301 is ideal for internal and external applications over plastered surfaces and fair face concrete. Dry Décor 301 is specially formulated to provide smooth finish when applied manually by trowel. Also, Dry Décor 301 can be applied by spraying machine or Tyrolean to increase productivity and color uniformity. In this case Dry Décor 301 will give rough finish surface.

Dry Decor 301 F is similar to Dry Decor 301 but formulated with micronized fillers that give an extra fine finished aspect

Composition:

Dry Decor 301 is manufactured from carefully selected raw materials which include a blend of special high strength hydraulic binders, well graded fillers, and special additives to enhance workability, water retention, adhesion and color stability against U.V and resistant to extreme weather conditions.

Uses

Advantages:

- Easy to use and apply. Only requires the addition of water on site for ease of use.
- Raw materials are selected according to the highest quality control standards.
- Exact mixing ratios and homogeneity of the blend, due to factory fully computerized production process.
- Available in wide range of uniform colors.
- Gives modern decorative finishing style.
- Excellent mixing and workability characteristics.
- The simplicity of usage and application gives very high productivity rates.
- Maximum protection against salt formation or efflorescence compared with conventional decorative renders.
- Excellent bonding characteristics to plastered substrates and fair face concrete.
- Breathable, allows the substrate to breath without de-lamination.
- Excellent resistance to extreme weather conditions.

Technical Data:

Bond Strength	1.0 N/mm ² .
Flexural Strength	> 3.3 N/mm ² .
Compressive Strength	> 10 N/mm ² .
Shrinkage	1.33 mm/m @ 28 days – Standard conditions
Water Absorption Coefficient	2.07 {kg/(m ² .h)}

Packaging:

Dry Décor 301 is available in 40 kg bags.

Mix Proportion

Approx. 9.2 ±0.25 litres of water/ 40 kg bag.

Coverage Rate:

2.25 – 2.5 Kg/m² (graviatto finish with hand trowel)
3.5 – 5 Kg/m² (rough texture with spray application).

(Coverage rate may vary depending on surface condition).

Surface Preparation:

- Cement based walls and ceilings are the recommended substrates that can be covered with Dry Décor 301. Plastered substrates should be left to cure for at least 14 days prior to application of Dry Décor 301.
- Any problem in the substrate which may lead to water penetration must be rectified.
- All surfaces should be in a good and strong condition.
- All surfaces should also be clean and free from any loose particles, dust, oil, grease, curing agents, or paint. If the surface is dry and in hot weather, pre-wet prior to the application of Dry Décor 301 without leaving excess water.

Application Procedures:

- Scaffolding must be fixed independently to allow for one go application.
- The whole contents of the bag should be mixed together with water, in one container using a hand drill equipped with mixing blade or high shear stationary mixer. Ask for our range of site mixers.
- Partial small amounts may be mixed manually, with a trowel, or other suitable hand mixing tools.
- Add 9.2 liters of fresh cool, clean water in one deep container. Then, add the contents of the 40 kg bag gradually and mix till the mixture is uniform and free of lumps. For best results, use as little water as possible. Keep mixing for 3 – 5 minutes, to insure proper mixing and good dispersion of additives.
- Dry Decor 301 should be immediately applied on the surface to be applied, while the mortar is fresh and workable. In case of delay, do not add additional water. Remix till the mortar is workable again.
- Apply Dry Decor 301 to the prepared surface either by conventional hand applied technique, Tyrolean or using spraying machine. Ask for our line of mixers and spraying machines.
- It is recommended to apply a scratch coat of the same mixed Dry Decor 301 prior to application of the final finish. The scratch coat should be left to set for 2 hours and pre-wetted prior to application of second coat. **Notes:** The scratch coat can be used as a recommendation in case of coat layer thicknesses exceeded 5mm for unlevelled plaster Or more than 8mm layer for sprays.
- Structure the layer with plastic or wooden trowel before the surface dries in order to reach the required architectural finish.
- To achieve color consistency, apply Dry Décor 301 in panels and complete it around the building.

Important Notes:

- Do not apply Dry Decor 301 on movement joints or on dynamic cracked plastered walls.
- Expansion joints should be included as per the substrate design and carried out through Dry Décor 301.
- Using cold water for mixing allows longer pot life and improved workability.
- Do not apply Dry Décor 301 over previously applied paints or gypsum plaster.
- It is advisable to seal the surfaces with a suitable sealer such as Dry Seal 860 to avoid inconsistent color finish, when applied on uneven or porous surfaces.
- It is recommended that Dry décor 301 should be stopped within 15 cm of the ground floor level and suitable skirting could be used to avoid dampness and discoloration.
- The quantity of mixing water should strictly be monitored between batches to ensure color uniformity, never remix with extra water. Should the mortar start to stiffen, just remix till the consistency gets back to a creamy, workable consistency again.
- To ensure color uniformity it is advisable to apply Dry Decor 301 in the shade, not in direct sun light.
- The work force should be enough to work on large areas, to eliminate cold joints and marks between different applications, it is advisable to apply large areas in one step, or split the large areas with grooved lines (Joints).
- Never cure with water or any curing compounds, as this may affect the color.
- In dusty areas subject to frequent splashes of water such as gardens, it might be advisable to treat the surface using Dry Seal 802, a water-repellent material, to be able to clean the stains easily.
- Applied colors may differ slightly from Dry Décor standard color chart due to job-site induced variations, such as application, drying, surface etc.
- As natural raw materials are used for the production of Dry Décor 301, it is advisable to apply the entire façade at one time to ensure color uniformity as minor variations might be observed sometimes

Storage:

Shelf life is 12 months from manufacturing date, in a dry, covered storage area.

Health and Safety:

While using the product, gloves and goggles should be worn.

Splashes to skin or eyes should be washed with clean water, in case of prolonged irritation, seek medical advice.