Technical Data Sheet PremierRepak 2206 High Temperature Silicone Sealant



PremierRepak 2206 is a one-component RTV (room temperature vulcanizing) acetoxy cure silicone adhesive/sealant, available only in RED. This product is designed for use in environments or applications in which high temperature performance is necessary. PremierRepak 2206 cures by reaction with moisture in the air to produce a durable, flexible, silicone rubber. The sealant can be applied at temperatures between -35°F (37°C) and 140°F (60°C). Cured material retains design properties and stays flexible for continuous use in the broader temperature range of -76°F (-60°C) to 500°F (260°C) with intermittent temperature performance up to 600°F (315.6°C). Cured sealant is resistant to sunlight, ultraviolet radiation, rain, sleet, snow, ozone and temperature extremes.

Applications:

PremierRepak 2206 has excellent adhesion to the following surfaces:

- Glass
- Cultured marble and ceramics
- Granite
- Tile
- Steel
- Aluminum
- Wood
- Plastics and fiberglass

Available colors: Red

Packaging: 10.1 fl.oz. HDPE standard caulk cartridges with foil seal.

<u>Listings & Specifications:</u> This product is FDA Regulation No. 21CFR 177.2600 Listed, UL QMFZ2, QMFZ8 Listed and NSF/ANSI Std 51 Certified.

Properties and Specifications:

Method As Supplied	<u>Test</u>	<u>Unit</u>	<u>Result</u>
ASTM C679	Tack Free Time	minutes	<= 25
	@ 25°C (77°F)		
	50% R.H.		
ASTM C603	Extrusion Rate	grams/min	250 to 500
	(Calculated)		
ASTM C792	Non-volatile content	% by wt.	>=85
ASTM C639	Flow, Sag or Slump	inches	<=0.20
	As Cured – 3 days at 25°C (77°F) and 50 %	R H	
ASTM D2240	Durometer, Shore A	points	>= 18
ASTIVI D2240	Hardness	points	> 10
ASTM D412	Ultimate Tensile Strength	psi	>= 170
ASTM D412	Elongation at Break	%	>= 350
ASTM C794	Peel Strength Low Carbon/S. Steel	ppi	>= 14
ASTM C794	Peel Strength Low Aluminum/Stn. Steel	ppi	>= 14



8351 185th Street • Tinley Park, IL 60487 • Ph: 855.737.2500 • Fx: 708.429.4280 www.premierrepak.com • customerservice@premierrepak.com

Technical Data Sheet PremierRepak 2206 High Temperature Silicone Sealant

Application Instructions:

- 1. Clean and dry the surface.
- 2. Cut nozzle to desired opening and puncture inner seal.
- 3. Apply with caulking gun holding at 45° angle and push sealant ahead of nozzle.
- 4. Complete tooling immediately after application and before "skin" forms. Remove excess sealant with dry paper towel
- 5. Normally, sealant "skins" in 5 minutes, dries to touch in 20 minutes and fully cures and bonds in 24 hours. Optimum strength is achieved in 3 days.
- 6. After sealant is completely cured, wash before use for food applications.
- 7. Sealant remaining in nozzle will cure. When ready to reuse, remove cured plug from nozzle. Remaining sealant is ready to use. Complete all painting prior to using sealant.

USE ENTIRE CONTENTS WITHIN SIX MONTHS AFTER OPENING.

Shelf Life: 24 months in original, unopened cartridge if stored below 90°F (32°C) in a dry place.

Joint width x depth	Estimated Usaş	
1/8" x ½"	48 feet	
¹ / ₄ " X ¹ / ₄ "	24 feet	
3/8" x ¹ / ₄ "	16 feet	
½" x 3/8"	8 feet	
5/8" x 7/16"	5.5 feet	
³ / ₄ " x ¹ / ₂ "	4 feet	

Foam backer rod, paper or suitable material is recommended to fill spaces where joint depth is expected to exceed 1/2 inch.

Limitations:

Not recommended for use in the following applications:

- Structural silicone glazing
- Temperatures in service higher than 600° F (315.6° C).
- Joints where physical abuse or abrasion is likely to be encountered
- Joints in excess of 3/4 inch in width and ½ inch in depth
- Prolonged water immersion
- Natural stone
- Copper, lead, galvanized metal
- · Porous surfaces such as masonry
- Surfaces or building materials that might bleed oils, plasticizers or solvents
- Impregnated wood, oil based caulks, green or partially vulcanized rubber gaskets or tapes
- Totally confined spaces, sealant requires moisture to cure
- Surfaces sensitive to corrosion by acetic acid vapors (a byproduct of sealant cure)
- Surfaces that will be painted (paint will not stretch with the extensions of the sealant and may crack and peel)
- Bonding to secondary seal of insulating glass units sealed with two-part silicone sealants.
- This product is not tested nor represented as suitable for medical, pharmaceutical or aerospace uses.

LIMITED WARRANTY

- It is the users responsibility to determine the suitability of any PremierRepak LLC product for his intended use or particular production requirement. Because the use of our products is beyond our control, we are not responsible for the results obtained.
- We make no warranties, expressed or implied, including the implied warranties of merchantability and fitness for a particular purpose and undertake and accept no liabilities, except as expressly set forth on our product labels. In every case, the Company's liability is limited to replacing such quantities of the product proven to be defective. The Company disclaims any liability for incidental, liquidated labor or any consequential damages arising from the use of products.
- No representative of the Company is authorized to grant any warranty or to waive this limitation of liability.
- The warranty provided herein and the obligation and liabilities of seller thereunder are exclusive and in lieu of and buyer hereby waives all other remedies, warranties, guarantees or liabilities, express or implied, arising by law or otherwise, including without limitation, any obligations of the seller with respect to consequential damages whether or not occasioned by seller's negligence. This warranty shall not be extended, altered or varied except by a written instrument signed by seller and buyer.



8351 185th Street • Tinley Park, IL 60487 • Ph: 855.737.2500 • Fx: 708.429.4280 www.premierrepak.com • customerservice@premierrepak.com